



## KORRODUR 1106

The all in one solution in rust preventing

KORRODUR 1106 combines all properties in just one product. The latest generation of water dilutable, solvent free rust preventing material comes without critical ingredients and is very easy to apply. A DTM coating is a direct to metal coating, which is the state-of-the-art in binder research and coating development.

Suitable for many surfaces, in all colors, from white to black, matt or shiny, for indoor and outdoor. KORRODUR 1106 direct to metal - rust prevention delivers the perfect product for each application.

### Application Instruction Tubing Coating

Surface Preparation:	Sand blasting metallic clean (class SA 2 <sup>1/2</sup> )
Base Coating:	1 x KORRODUR 1106, white <sup>(1)</sup> Consumption <sup>(3)</sup> app. 200 g/m <sup>2</sup>
Intermediate Layer:	1 x KORRODUR 1106 tinted color <sup>(2)</sup> Consumption <sup>(3)</sup> app. 150g/m <sup>2</sup>
Topcoat:	1 x KORRODUR 1106 white <sup>(1)</sup> Consumption <sup>(3)</sup> app. 150g/m <sup>2</sup>

(1) or any other color

(2) for better control, tint intermediate layer e.g. light grey

(3) recommended minimum consumption, without overspray

### Processing

KORRODUR 1106 is structure viscous and ready to use. Aireless pumps are especially suitable in case of spray application. Additionally thinning is not recommended, but possible. A suitable thinner is demineralized water. Manual application with usual painter equipment (brush, roll and painting brush)

Special work protective measurements are not necessary.

Equipment, tools and pumps could be cleaned with normal tap water.

These technical information describe the present-day state of knowledge these product. They should only inform about the possibilities of application and could not release the applicator of his commitment to check the possibility to use the product for the required application. Information for processing can be found in processing instructions of our product. Information about safe handling can be found in our current safety data sheet.

ATI-1106 | 05 - 2021 | V1  
© ARCAN GmbH  
All rights reserved

### ARCAN Waterproof

ARCAN GmbH Spezialbaustoffe

Kleinniedesheimer Strasse 19  
D-67240 Bobenheim-Roxheim  
Phone: +49 (0)6239 - 99 78 20  
Mail: [office@arcan.biz](mailto:office@arcan.biz)  
Web: [www.arcan.biz](http://www.arcan.biz)

passion to invent 