

## Rokryl®Rapid 333

Fast grout and repair mortar for asphalt coverings

Elastic, abrasion proof and excellent adhesion on the surface. It is resistant against oil, fuel and de-icing salt. The hardening time is 20 minutes and it is easy to use.

It is an AC reaction resin mortar made of binding agent which is developed by us and hard mineral materials. With excellent adhesion on typical coverings used for roadworks, on rolled asphalt, melted asphalt, on stone and concrete. Perfect for all repairworks of industrial floors, traffic areas, airfields and runways, as compound, for pile grouting and more. Processing at frost temperatures is possible!

### Product data

Liquid component A	Monomere and polymere methacrylate
Aspect	Unclear liquid with weak odour
Solid component B	Mixture of mineral materials and additives
Mixing ratio	A to B = 3-4 :10 (recommended)
Shelf life	1 year if stored dry and cool

### Mortar properties

Processing time -tG-	Approx. 10 minutes at 20°
Category temperature	-10 up to. +35°
Setting time	Approx 20 minutes at 20°
Colour	Black grey
Density	1,8 g/ml
Compressive strength	60 - 70 N/mm <sup>2</sup>
Bending tensile strength	20 N/mm <sup>2</sup>

### Processing

The surface must be hard enough, stable and free of dust. Remove pollutions always complete!

Mix the mortar of both component with a mixing machine ( for example by drilling machine). The recommended mixing ratio (10 parts solid material : 3-4 parts resin) is not critical. The consistency of the mortar can be adjusted to the situation on the building site. The mortar should be of paste-like consistency and not dry. Avoid earth-moist mixtures. The embedded air can disturb the hardening process!

For both components are safety data sheets available. They contain all relevant informations for safe handling of our products and can be requested on demand.

These technical information describe the present-day state of knowledge these product. They should only inform about the possibilities of application and could not release the applicator of his commitment to check the possibility to use the product for the required application. Information for processing can be found in processing instructions of our product. Information about safe handling can be found in our current safety data sheet.

ATI-Rokryl®Rapid 333  
© ARCAN GmbH  
All rights reserved

### ARCAN Waterproof

ARCAN GmbH Spezialbaustoffe

Kleinniedesheimer Strasse 19  
D-67240 Bobenheim-Roxheim  
Phone: +49 (0)6239 - 99 78 20  
Mail: [office@arcan.biz](mailto:office@arcan.biz)  
Web: [www.arcan.biz](http://www.arcan.biz)

passion to invent 